TECAPRO® MT black - Stock Shapes

Chemical Designation

PP (Polypropylene)

Colour black

DIACK

Density 0.92 g/cm³

Main features

- → heat stabilized
- → autoclavable
- → biocompatible
- good chemical resistance
- hydrolysis and superheated steam
- resistant → low moisture absorption
- → good slide and wear properties

Target Industries

- medical technology
- pharmaceutical industry

Ensinger **o**

→ food engineering

Mechanical properties	condition	value		test method		comment
Tensile strength at yield	@ 73 °F	5076	psi	ASTM D 638		
Elongation at break	@ 73 °F	12	%	ASTMD 638		
Flexural strength	@ 73 °F	7830	psi	ASTM D 790		
Modulus of elasticity (flexural test)	@ 73 °F	210,000	psi	ASTMD 790		
Compression strength	1% Sec, @ 73 °F	2320	psi	ASTMD 695		
Compression modulus		232000	psi	ASTM D 695	_	
Impact strength (Izod)	@ 73 °F	0.899	ft-lbs/in	ASTMD 256		
Thermal properties	condition	value		test method		comment
Melting temperature		325	°F	-	1)	(1) per ASTM D789
Deflection temperature	@264 psi	187	°F	ASTM D 648		
Service temperature	Intermittent	284	°F	-		
Service temperature	Long Term	212	°F	-		

 Resin specification: ASTM D 4101 PP0110 Shapes specification: None

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters 365 Meadow lands Boulevard Washington, PA 15301, USA Phone 800-243-3221 Sales Phone 800-869-4029 Technical Fax 724-746-9209 sales@ensinger-ind.com Date: 2017/08/15

Version: