

The Multi-Color Engravable Polymer Sheet

King ColorCore[®] is a versatile, environmentally stabilized sheet with multiple layers of contrasting colors. Its thin cap layers and bright primary colors make it ideal for signage, marine, playground and recreational applications. For maximum versatility, standard colors are made to coordinate with King ColorBoard[®]. King ColorCore[®] is easy to engrave and machine, as the cap is approximately .050" thick. King ColorCore[®] is made with high-impact-resistant polymer to handle more abuse than conventional sign materials. It will not warp, rot or delaminate. King ColorCore[®] is a superior homogeneous sheet, made with a unique state-of-the-art continuous process called Polyfusion, manufactured to the highest standards in the industry. Base materials are FDA approved.

King ColorCore[®] is upgradable to King MicroShield[®] with an advanced antimicrobial technology for protecting the product surface against stain and odor causing bacteria, algae and fungi.^{*}

For more information about King MicroShield[®], please visit www.kingplastic.com

Engraving Products



Applications

- Architectural Applications
- Carnival Games
- Children's Furniture
- Furniture
- Marine Applications
- Museums
- Picnic Tables
- Point-of-Purchase Displays
- Signage and Wayfinding

| Specifications | | Standard Colors | | |
|--|-----------------|------------------|---|---|
| Standard Sheet Size in: 48" x 96" mm: 1219mm x 2438mm | Blue/White/Blue | White/Blue/White | Red/White/Red | White/Red/White |
| Standard Gauges in: 1/4" 1/2" 3/4" mm: 6.4mm 12.7mm 19mm | Red/Black/Red | Black/Red/Black | Green/White/Green | White/Green/White |
| Approximate Weight lbs: 40 lbs 80 lbs 120 lbs kg: 18kg 36kg 54kg | Green/Tan/Green | Tan/Green/Tan | Yellow/Black/Yellow | Black/Yellow/Black |
| Cap thickness is .050" for both sides of the material Tolerance information: Gauges 1/4" up to 3/4" ± 5% Length and width plus only at room temperature Custom sheet sizes, gauges, and colors available | Brown/Tan/Brown | Tan/Brown/Tan | Brown/White/Brown Note: Color accuracy co on computer monitors consult your distributo sample before making Disclaimer: King Micro | and printers. Please or for a product critical color choices. |

*For bacteriostatic, fungistatic, & algistatic properties. This product is exempt from registration under 40 CFR 152.25(a). King MicroShield® effectiveness verified by ISO and ASTM standards. This product does not protect users or others from disease-causing bacteria. Always clean this product thoroughly after use.

| Properties | Units | ASTM | Nominal Values |
|-----------------------------------|--------------------------|-------|-----------------------|
| Density | g/cc | D1505 | 0.955 |
| Tensile Strength @ Yield | psi | D638 | >4,100 |
| Tensile Modulus | psi | D638 | 255,000 |
| Elongation @ Yield | % | D638 | 9.8 |
| Elongation @ Break | % | D638 | >600 |
| Flexural Modulus | psi | D790 | 185,000 |
| Flexural Stress @ 5% Strain | psi | D790 | 3,810 |
| Compressive Properties 10% Strain | psi | D695 | 4,950 |
| Durometer | Shore D | D2240 | 68 |
| Tensile Impact | ft.lbs./in. ² | D1822 | 115 |
| Izod Impact Resistance | ft.lbs./in. ² | D256 | 1.1 |
| Brittleness Temp. | °C (°F) | D746 | <-76°C (<-105°F) |
| Vicat Softening Temp. | °C (°F) | D1525 | 123°C (253°F) |
| Heat Deflection Temp. 66 psi | °C (°F) | D648 | 75°C (167°F) |
| Screw and Nail Withdrawal | lbs | D1761 | 657 & 63 |
| Flammability | Rating | UL94 | HB |

All values are determined on specimens prepared according to ASTM Standards. Nominal values should not be interpreted as specifications. King ColorCore® is made entirely from FDA and USDA approved material.

King ColorCore® meets ASTM D4976. The raw material used to make King ColorCore® does not contain BPA's or Phthalates.



1100 N. Toledo Blade Blvd. | North Port, FL 34288 USA P: 941.493.5502 | F: 941.497.3274 | www.kingplastic.com